



## FVG PREMIUM Poly Patch®

Repair tape with original  
greenhouse film “FVG Sun Clear”



Product description	uv stable, 550 KLY = 5 years of 110 kly in central Europe		
Colour	transparent		
Thickness	Film: 180µ	adhesive quantity: 200g/qm	
Tensile Strength	EN ISO 527-3	MD 26 N/mm <sup>2</sup>	TD 28 N/mm <sup>2</sup>
Elongation at break	EN ISO 527-3	MD 550%	TD 650%
Dart drop	ISO 7765-1 (A)	Fold: >1000	flat:>1000
Total transmission	EN 2155-5	ca. 91%	
UV B transmission	Internal Test	>70 %	
Light Diffusion	EN 2155-9	app. 18% (400-700nm)	
Thermicity/ IR	EN13206	app. 50 %	
Adhesive power	AFERA 5001 N/25mm	ca. 45 N/25 mm	
Dimensions	8cm x 20m / 16cm x 20m		

- application in temperatures from +80 / -40 °C
- storage temperature 20 – 30 °C and max. air humidity of 65% in original package

FVG warrants that this product conforms to its specifications. The test results are being provided based on current production. Products warranty is based on FVG Warranty terms for greenhouse film and installation /handling guidelines. Buyer is responsible to verify the suitability of the product for his particular use. The amount of any claim against FVG and FVG's liability relative to the product's properties or performance, shall in no event exceed the purchase value of the product. In no event shall FVG be liable for loss of profit or special, indirect or consequential damages. Since the mechanism of action of the anti-dripping and anti-fogging effect as well as the reduction of insects and petal blackening are complicated and depend on many parameters that are out of control (climatic conditions, greenhouse type, crop, pollination method etc.), no warranty is given regarding the duration or effectiveness of these functions and we do not undertake liability for any damage relevant to those functions. More information at [www.fvg-folien.de](http://www.fvg-folien.de)